

SPECIFICATION / SPESIFIKASI / 规格

Properties / Kandungan / 特性	MS EN 413-1:2012 MC 12.5
Fineness - 90 um Residue (%) <i>Kehalusan - 90 um Residue (%)</i> 细度 - 90 um 余留 (%)	15 Max
Initial Setting Time (minutes) <i>Masa Penetapan Permulaan (minit)</i> 初凝时间 (分钟)	60 Min
Sulphuric Anhydride, SO ₃ (%) <i>Kandungan Sulfat, SO₃ (%)</i> 三氧化硫含量, SO ₃ (%)	3.5 Max
Chloride Content, Cl (%) <i>Kandungan Klorida, Cl (%)</i> 氯离子含量, Cl (%)	0.10 Max
Air Content (%) <i>Kandungan Udara (%)</i> 空气含量 (%)	8 - 22
Water Retention (%) <i>Pengekalan Air (%)</i> 保水率 (%)	80 Min
Soundness (Expansion) (mm) <i>Kekukuhan (Pengembangan) (mm)</i> 稳健性 (膨胀) (mm)	10 Max
Compressive Strength / <i>Kekuatan Mampatan</i> / 抗压强度 7 days / <i>hari</i> / 天 (N/mm ²) 28 days / <i>hari</i> / 天 (N/mm ²)	7 Min 12.5 - 32.5

Specification of product is subjected to manufacturer's change without prior notice.
Spesifikasi produk adalah tertakluk pada perubahan oleh pengeluar tanpa notis awal.
厂商有权更改产品规格, 无需另行通知。

Recommended Mix Proportion / <i>Jumlah Campuran Yang Disyorkan</i> / 推荐的混合比例			
Application / <i>Applikasi</i> 应用	Parts of Tasek Masonry Cement / <i>Jumlah Isipadu Tasek Masonry Cement</i> 所需的大石牌砌砖水泥分量 (KG)	Parts of Sand By Volume / <i>Jumlah Isipadu Pasir</i> 所需的沙份量	
Plastering / <i>Kerja Plaster</i> 涂灰	1	Min / 最少	Max / 最多
		3	5

PACKAGING / PEMBUNGKUSAN / 包装

50kg bag / Beg 50kg / 50公斤包装

Tasek Corporation Berhad

HEAD OFFICE & FACTORY

Lot 5, Persiaran Tasek, Tasek Industrial Estate,
31400 Ipoh, Perak, Malaysia

Tel: +605 290 9000

Fax: +605 291 9932

✉ info@tasek.com.my

SALES AND MARKETING OFFICE &

DISTRIBUTION TERMINAL

Lot 1552, Kg. Jaya Industrial Area, Off Jalan Hospital,
47000 Sungai Buloh, Selangor, Malaysia

Tel: +603 6156 6818

✉ marketing@tasek.com.my



SIRIM
MS EN 413-1 : 2012
PT020302



www.tasek.com.my

TERRAPLAS®

MASONRY CEMENT



www.tasek.com.my

TASEK
A Hong Leong Asia Company

TERRAPLAS®

MASONRY CEMENT

TERRAPLAS® is the brand name for masonry cement specially formulated and manufactured to achieve the required properties and workability for plastering purposes. It is produced by using high quality Portland cement clinker grinding with plasticizing materials and air entraining agent in a controlled environment to assure product consistency and performance.

TERRAPLAS® complies with the Malaysian Standard MS EN 413-1:2012.

TERRAPLAS® adalah jenama simen penampal yang dirumus khas dan dihasilkan untuk mencapai sifat-sifat dan kebolehterkerjaan untuk kerja-kerja penampalan. TERRAPLAS® dihasilkan dengan mengisarkan klinker simen Portland serta bahan-bahan plaster dan agen pengedap udara dalam keadaan yang terkawal untuk memastikan kualiti produk yang konsisten.

TERRAPLAS® menepati piawaian yang ditetapkan oleh Standard Malaysia MS EN 413-1:2012.

TERRAPLAS® 是大石公司生产的砌筑水泥品牌。它的独特配方使它有效的提高工作性。TERRAPLAS® 采用了高品质的水泥熟料,可塑料和引气剂研磨而成以确保产品的品质和一致性。

TERRAPLAS® 符合马来西亚标准局MS EN 413-1:2012 的标准和规格。

MASONRY CEMENT



Applications / Penggunaan / 产品用途

It is highly recommended for interior and exterior plastering works.
Sesuai digunakan untuk kerja penampalan plaster dalaman dan luaran.
极力推荐用于户内, 户外抹灰和外墙修饰。

Advantages / Kelebihan / 产品优点

- Easy to mix / Senang diguna / 容易使用
- Good workability / Kebolehterkerjaan yang baik / 提高工作性
- Good bonding / Lekatan yang baik / 良好的粘接
- Improved surface finishing / Meningkatkan kelicinan hasil permukaan / 表面平滑修整

